




万博丝网

黄铜网




平纹编织

黄铜网

平纹编织


平纹编织

每根经丝交叉地在每根纬丝上下穿过，径丝和纬丝一样粗细，经线和纬线成 90 度角的编织方式。



孔径 (w)

相邻两个平行丝径之间的距离，不包含丝径的尺寸。



丝径 (d)

目数

指编织网密度的值，每英寸中编织丝网的网孔数

$$\text{目数} = \frac{25.4 \text{ mm}}{w \text{ (mm)} + d \text{ (mm)}}$$

开孔率 (A)

开孔率的百分比计算公式：

$$A = \left(\frac{w}{w+d} \right)^2 \times 100\%$$



黄铜网

平纹编织

| 目数 | 丝径 | | 孔径 | | 开孔率 % | 开孔面积 mm ² | 重量 | |
|----|------|--------|-------|--------|----------|-------------------------|--------------------|--------------------|
| | mm | inch | mm | inch | | | kgs/m ² | lbs/m ² |
| 6 | 0.4 | 0.0157 | 3.833 | 0.1509 | 81.99 | 14.6944 | 0.54 | 1.19 |
| | 0.5 | 0.0196 | 3.733 | 0.1469 | 77.77 | 13.9377 | 0.85 | 1.86 |
| | 0.6 | 0.0236 | 3.633 | 0.143 | 73.66 | 13.2011 | 1.22 | 2.68 |
| | 0.7 | 0.0275 | 3.533 | 0.1391 | 69.66 | 12.4844 | 1.66 | 3.65 |
| 8 | 0.4 | 0.0157 | 2.775 | 0.1092 | 76.39 | 7.7006 | 0.72 | 1.59 |
| | 0.5 | 0.0196 | 2.675 | 0.1053 | 70.98 | 7.1556 | 1.13 | 2.49 |
| 10 | 0.35 | 0.0138 | 2.19 | 0.086 | 74.3 | 4.8 | 0.69 | 1.52 |
| | 0.4 | 0.0157 | 2.140 | 0.0842 | 70.98 | 4.5796 | 0.90 | 1.99 |
| | 0.5 | 0.0196 | 2.040 | 0.0803 | 64.50 | 4.1616 | 1.41 | 3.11 |
| 12 | 0.35 | 0.0138 | 1.77 | 0.07 | 69.66 | 3.12 | 0.84 | 1.83 |
| | 0.4 | 0.0157 | 1.716 | 0.0675 | 65.77 | 2.9469 | 1.09 | 2.39 |
| | 0.5 | 0.0196 | 1.616 | 0.0636 | 58.33 | 2.6136 | 1.70 | 3.72 |
| 14 | 0.3 | 0.0118 | 1.514 | 0.0596 | 69.66 | 2.2930 | 0.71 | 1.56 |
| | 0.35 | 0.0137 | 1.464 | 0.0576 | 65.13 | 2.1441 | 0.96 | 2.11 |
| | 0.4 | 0.0157 | 1.414 | 0.0556 | 60.76 | 2.0002 | 1.27 | 2.78 |
| | 0.5 | 0.0196 | 1.314 | 0.0517 | 52.47 | 1.7273 | 1.98 | 4.35 |
| 16 | 0.25 | 0.0098 | 1.337 | 0.0526 | 70.98 | 1.7889 | 0.57 | 1.25 |
| | 0.27 | 0.0106 | 1.317 | 0.0518 | 68.87 | 1.7358 | 0.66 | 1.43 |
| | 0.40 | 0.0157 | 1.187 | 0.0467 | 55.95 | 1.4101 | 1.44 | 3.18 |

黄铜网

平纹编织

| 目数 | 丝径 | | 孔径 | | 开孔率 | 开孔面积 | 重量 | |
|----|------|--------|--------|--------|-------|--------|------|-----------------|
| | mm | inch | mm | inch | | | % | mm ² |
| 18 | 0.15 | 0.0059 | 1.2611 | 0.0496 | 79.87 | 1.5904 | 0.23 | 0.50 |
| | 0.17 | 0.0066 | 1.2411 | 0.0488 | 77.35 | 1.5403 | 0.29 | 0.65 |
| | 0.19 | 0.0074 | 1.2211 | 0.048 | 74.88 | 1.4911 | 0.37 | 0.81 |
| | 0.21 | 0.0082 | 1.2011 | 0.0472 | 72.45 | 1.4426 | 0.44 | 0.98 |
| | 0.25 | 0.0098 | 1.161 | 0.0457 | 67.7 | 1.3481 | 0.63 | 1.39 |
| | 0.30 | 0.0118 | 1.111 | 0.0437 | 62 | 1.2345 | 0.91 | 2.01 |
| | 0.4 | 0.0157 | 1.0111 | 0.0398 | 51.34 | 1.0223 | 1.63 | 3.57 |
| 20 | 0.19 | 0.0074 | 1.080 | 0.0425 | 72.31 | 1.1664 | 0.41 | 0.89 |
| | 0.21 | 0.0082 | 1.060 | 0.0417 | 69.66 | 1.1236 | 0.50 | 1.10 |
| | 0.25 | 0.0098 | 1.020 | 0.0401 | 64.50 | 1.0404 | 0.70 | 1.54 |
| | 0.30 | 0.0118 | 0.970 | 0.0381 | 58.33 | 0.9409 | 1.01 | 2.24 |
| | 0.4 | 0.0157 | 0.87 | 0.0342 | 46.92 | 0.7569 | 1.81 | 3.98 |
| 22 | 0.25 | 0.0098 | 0.904 | 0.0356 | 61.38 | 0.8182 | 0.76 | 1.68 |
| 24 | 0.15 | 0.0059 | 0.908 | 0.0357 | 73.66 | 0.825 | 0.30 | 0.67 |
| | 0.20 | 0.0078 | 0.858 | 0.0337 | 65.77 | 0.7367 | 0.54 | 1.19 |
| | 0.30 | 0.0118 | 0.758 | 0.0298 | 51.34 | 0.5750 | 1.22 | 2.68 |
| | 0.35 | 0.0137 | 0.708 | 0.0278 | 44.79 | 0.5017 | 1.66 | 3.65 |

黄铜网 平纹编织

| 目数 | 丝径 | | 孔径 | | 开孔率 % | 开孔面积 mm ² | 重量 | |
|----|------|--------|-------|--------|----------|-------------------------|--------------------|--------------------|
| | mm | inch | mm | inch | | | kgs/m ² | lbs/m ² |
| 30 | 0.12 | 0.0047 | 0.726 | 0.0286 | 73.66 | 0.5280 | 0.24 | 0.53 |
| | 0.13 | 0.0051 | 0.716 | 0.0282 | 71.64 | 0.5136 | 0.28 | 0.62 |
| | 0.15 | 0.0059 | 0.696 | 0.0274 | 67.7 | 0.4853 | 0.38 | 0.84 |
| | 0.17 | 0.0066 | 0.676 | 0.0266 | 63.87 | 0.4578 | 0.48 | 1.08 |
| | 0.19 | 0.0074 | 0.656 | 0.0258 | 60.15 | 0.4312 | 0.61 | 1.33 |
| | 0.20 | 0.0078 | 0.646 | 0.0254 | 58.33 | 0.4181 | 0.68 | 1.50 |
| | 0.27 | 0.0106 | 0.576 | 0.0227 | 46.39 | 0.3325 | 1.23 | 2.71 |
| 40 | 0.12 | 0.0047 | 0.515 | 0.0202 | 65.77 | 0.2652 | 0.32 | 0.71 |
| | 0.15 | 0.0059 | 0.485 | 0.0190 | 58.33 | 0.2352 | 0.51 | 1.12 |
| | 0.18 | 0.0070 | 0.455 | 0.0179 | 51.34 | 0.2070 | 0.73 | 1.61 |
| | 0.20 | 0.0078 | 0.435 | 0.0171 | 46.92 | 0.1892 | 0.90 | 1.98 |
| 50 | 0.12 | 0.0047 | 0.388 | 0.0152 | 58.33 | 0.1505 | 0.41 | 0.89 |
| | 0.13 | 0.0051 | 0.378 | 0.0148 | 55.36 | 0.1428 | 0.47 | 1.04 |
| | 0.15 | 0.0059 | 0.358 | 0.0140 | 49.66 | 0.1281 | 0.63 | 1.39 |
| | 0.20 | 0.0078 | 0.308 | 0.0121 | 36.75 | 0.0948 | 1.13 | 2.49 |
| 60 | 0.10 | 0.0039 | 0.323 | 0.0127 | 58.30 | 0.1043 | 0.33 | 0.74 |
| | 0.11 | 0.004 | 0.313 | 0.0123 | 54.76 | 0.09797 | 0.41 | 0.90 |
| | 0.12 | 0.0047 | 0.303 | 0.0119 | 51.34 | 0.0920 | 0.48 | 1.08 |
| | 0.15 | 0.0059 | 0.273 | 0.0107 | 41.68 | 0.0747 | 0.75 | 1.66 |

黄铜网

平纹编织

| 目数 | 丝径 | | 孔径 | | 开孔率 % | 开孔面积 mm ² | 重量 | |
|-----|---------|--------|-------|--------|----------|-------------------------|--------------------|--------------------|
| | mm | inch | mm | inch | | | kgs/m ² | lbs/m ² |
| 60 | 0.17 | 0.0066 | 0.253 | 0.0099 | 35.81 | 0.0641 | 0.97 | 2.14 |
| | 0.19 | 0.0074 | 0.233 | 0.0091 | 30.38 | 0.0544 | 1.22 | 2.68 |
| 80 | 0.08 | 0.032 | 0.237 | 0.0093 | 55.72 | 0.0561 | 0.29 | 0.65 |
| | 0.09 | 0.0035 | 0.227 | 0.0089 | 51.34 | 0.0517 | 0.37 | 0.81 |
| | 0.10 | 0.0039 | 0.217 | 0.0085 | 46.92 | 0.0473 | 0.45 | 0.99 |
| | 0.12 | 0.0047 | 0.197 | 0.0077 | 38.69 | 0.0390 | 0.65 | 1.41 |
| 100 | 0.07 | 0.0027 | 0.184 | 0.0072 | 52.48 | 0.0339 | 0.27 | 0.61 |
| | 0.08 | 0.0031 | 0.174 | 0.0068 | 46.92 | 0.0302 | 0.37 | 0.80 |
| | 0.09123 | 0.0035 | 0.164 | 0.0064 | 41.69 | 0.0269 | 0.46 | 1.00 |
| | 0.10 | 0.0039 | 0.154 | 0.0060 | 36.75 | 0.0237 | 0.57 | 1.25 |
| 120 | 0.05 | 0.0020 | 0.162 | 0.0064 | 58.34 | 0.0261 | 0.17 | 0.38 |
| | 0.06 | 0.0024 | 0.152 | 0.0060 | 51.34 | 0.0230 | 0.24 | 0.53 |
| | 0.07 | 0.0028 | 0.142 | 0.0056 | 44.80 | 0.0201 | 0.33 | 0.73 |
| | 0.08 | 0.0031 | 0.132 | 0.0052 | 38.69 | 0.0173 | 0.37 | 0.80 |
| 150 | 0.06 | 0.0023 | 0.109 | 0.0043 | 41.68 | 0.0119 | 0.30 | 0.67 |
| | 0.07 | 0.0027 | 0.099 | 0.0039 | 34.41 | 0.0098 | 0.41 | 0.90 |
| 180 | 0.05 | 0.0019 | 0.091 | 0.0035 | 41.68 | 0.0083 | 0.25 | 0.54 |
| | 0.06 | 0.0023 | 0.081 | 0.0031 | 33.03 | 0.0065 | 0.36 | 0.78 |
| 200 | 0.05 | 0.0019 | 0.077 | 0.0030 | 36.75 | 0.0059 | 0.28 | 0.62 |

黄铜网
平纹编织



安平工厂图

总公司

万博丝网有限公司

河北省安平县丝网工业园东区纬二路 12 号

电话：0318-7568801

传真：0318-7568802

网址：www.webmeshgroup.com

分公司

万博丝网有限公司---石家庄分公司

河北省石家庄市新华区橙悦城

电话：0311-89255081

传真：0311-89255081

网址：www.webmeshgroup.com