


钢网




平纹编织

钢网

平纹编织


平纹编织

每根经丝交叉地在每根纬丝上下穿过，径丝和纬丝一样粗细，经线和纬线成 90 度角的编织方式。



孔径 (w)

相邻两个平行丝径之间的距离，不包含丝径的尺寸。



丝径 (d)

目数

指编织网密度的值，每英寸中编织丝网的网孔数

$$\text{目数} = \frac{25.4 \text{ mm}}{w \text{ (mm)} + d \text{ (mm)}}$$

开孔率 (A)

开孔率的百分比计算公式：

$$A = \left(\frac{w}{w+d} \right)^2 \times 100\%$$



钢网

平纹编织

目数	丝径		孔径		开孔率	开孔面积	重量	
	mm	inch	mm	inch			%	mm ²
3	1.6	0.0629	6.866	0.2703	65.77	47.1511	3.84	8.44
	1.4	0.0551	7.066	0.2782	69.66	49.9377	2.94	6.46
	1.2	0.0472	7.266	0.2860	73.66	52.8044	2.16	4.75
	1.00	0.0393	7.466	0.2939	77.77	55.7511	1.50	3.30
	0.9	0.0354	7.566	0.2979	79.87	57.2544	1.21	2.67
	0.80	0.0314	7.666	0.3018	81.99	58.7777	0.96	2.11
	0.70	0.0275	7.766	0.3057	84.14	60.3211	0.73	1.60
4	1.2	0.0472	5.15	0.2027	65.77	26.5225	2.88	6.33
	1.0	0.0393	5.35	0.2106	70.98	28.6225	2	4.4
	0.9	0.0354	5.45	0.2145	73.66	29.7025	1.62	3.56
	0.80	0.0314	5.550	0.2185	76.39	30.8025	1.28	2.81
	0.70	0.0275	5.650	0.2224	79.16	31.9225	0.98	2.15
	0.60	0.0236	5.750	0.2263	81.99	33.0625	0.72	1.58
5	1.0	0.0393	4.08	0.1606	64.50	16.6464	2.5	5.5
	0.9	0.0354	4.18	0.1645	67.70	17.4724	2.02	4.45
	0.80	0.0314	4.280	0.1685	70.98	18.3184	1.60	3.52
	0.70	0.0275	4.380	0.1724	74.33	19.1844	1.22	2.68
	0.6	0.0236	4.48	0.1763	77.77	20.0704	0.9	1.98

钢网 平纹编织

目数	丝径		孔径		开孔率 %	开孔面积 mm ²	重量	
	mm	inch	mm	inch			kgs/m ²	lbs/m ²
5	0.5	0.0196	4.58	0.1803	81.28	20.9764	0.62	1.37
	0.9	0.0354	3.3333	0.1312	62.00	11.1111	2.43	5.34
6	0.8	0.0314	3.4333	0.1351	65.77	11.7877	1.92	4.22
	0.70	0.0275	3.533	0.1391	69.66	12.4844	1.47	3.23
	0.60	0.0236	3.633	0.1430	73.66	13.2011	1.08	2.37
	0.5	0.0196	3.733	0.1469	77.77	13.9377	0.75	1.65
8	0.9	0.0354	2.275	0.0895	51.34	5.1756	3.24	7.12
	0.8	0.0314	2.375	0.0935	55.95	5.6406	2.56	5.63
	0.7	0.0275	2.475	0.0974	60.76	6.1256	1.96	4.31
	0.6	0.0236	2.575	0.1013	65.77	6.6306	1.44	3.16
	0.50	0.0196	2.675	0.1053	70.98	7.1556	1.00	2.20
10	0.9	0.0354	1.64	0.0645	41.68	2.6896	4.05	8.91
	0.8	0.0314	1.74	0.0685	46.92	3.0276	3.2	7.04
	0.7	0.0275	1.84	0.0724	52.47	3.3856	2.45	5.39
	0.6	0.0236	1.94	0.0763	58.33	3.7636	1.8	3.96
	0.50	0.0196	2.040	0.0803	64.50	4.1616	1.25	2.75
	0.40	0.0157	2.140	0.0842	70.98	4.5796	0.80	1.76

钢网 平纹编织

目数	丝径		孔径		开孔率 %	开孔面积 mm ²	重量	
	mm	inch	mm	inch			kgs/m ²	lbs/m ²
12	0.8	0.0314	1.3166	0.0518	38.69	1.7336	3.84	8.44
	0.7	0.0275	1.4166	0.0557	44.79	2.0069	2.94	6.46
	0.6	0.0236	1.5166	0.0597	51.34	2.3002	2.16	4.75
	0.50	0.0196	1.616	0.0636	58.33	2.6136	1.50	3.30
	0.40	0.0157	1.716	0.0675	65.77	2.9469	0.96	2.11
	0.30	0.0118	1.8166	0.0715	73.66	3.3002	0.54	1.18
14	0.7	0.0275	1.1142	0.0438	37.72	1.2416	3.43	7.54
	0.6	0.0236	1.2142	0.0478	44.79	1.4744	2.52	5.54
	0.50	0.0196	1.314	0.0517	52.47	1.7273	1.75	3.85
	0.40	0.0157	1.414	0.0556	60.76	2.0002	1.12	2.46
	0.35	0.0137	1.464	0.0576	65.13	2.1441	0.85	1.87
	0.30	0.0118	1.5142	0.0596	69.66	2.2930	0.63	1.38
	0.27	0.0106	1.5442	0.0607	72.45	2.3848	0.51	1.12
	0.25	0.0098	1.564	0.0615	74.33	2.4469	0.43	0.94
	0.23	0.0090	1.5842	0.0623	76.25	2.5099	0.37	0.81
	0.21	0.0082	1.6042	0.0631	78.19	2.5737	0.30	0.67
0.19	0.0074	1.624	0.0639	80.15	2.6383	0.25	0.55	

钢网 平纹编织

目数	丝径		孔径		开孔率 %	开孔面积 mm ²	重量	
	mm	inch	mm	inch			kgs/m ²	lbs/m ²
16	0.6	0.0236	0.9875	0.0388	38.69	0.9751	2.88	6.33
	0.5	0.0196	1.0875	0.0428	46.92	1.1826	2	4.4
	0.4	0.0157	1.1875	0.0467	55.95	1.4101	1.28	2.816
	0.35	0.0137	1.237	0.0487	60.76	1.5314	0.98	2.15
	0.30	0.0118	1.2875	0.0506	65.77	1.6576	0.72	1.58
	0.27	0.0106	1.317	0.0518	68.87	1.7358	0.58	1.27
	0.25	0.0098	1.337	0.0526	70.98	1.7889	0.50	1.10
	0.23	0.0090	1.357	0.0534	73.12	1.8428	0.42	0.92
	0.21	0.0082	1.3775	0.0542	75.29	1.8975	0.35	0.77
	0.19	0.0074	1.397	0.0550	77.49	1.9530	0.28	0.61
18	0.50	0.0196	0.9111	0.0358	41.68	0.8301	2.25	4.95
	0.40	0.0157	1.0111	0.0398	51.34	1.0223	1.44	3.16
	0.35	0.0137	1.061	0.0417	56.54	1.1259	1.10	2.42
	0.30	0.0118	1.111	0.0437	62.00	1.2345	0.81	1.78
	0.27	0.0106	1.1411	0.0449	65.39	1.3021	0.65	1.44
	0.25	0.0098	1.161	0.0457	67.70	1.3481	0.56	1.23
	0.23	0.0090	1.1811	0.0465	70.05	1.3950	0.47	1.04
	0.21	0.0082	1.2011	0.0472	72.45	1.4426	0.39	0.87

钢网 平纹编织

目数	丝径		孔径		开孔率	开孔面积	重量	
	mm	inch	mm	inch			%	mm ²
18	0.19	0.0074	1.2211	0.0480	74.88	1.4911	0.32	0.71
	0.17	0.0066	1.2411	0.0488	77.35	1.5403	0.26	0.57
	0.15	0.0059	1.2611	0.0496	79.87	1.5904	0.20	0.44
20	0.50	0.0196	0.770	0.0303	36.75	0.5929	2.50	5.50
	0.45	0.0177	0.820	0.0322	41.68	0.6724	2.02	4.44
	0.40	0.0157	0.87	0.0342	46.92	0.7569	1.6	3.52
	0.35	0.0137	0.92	0.0362	52.47	0.8464	1.22	2.69
	0.30	0.0118	0.970	0.0381	58.33	0.9409	0.90	1.98
	0.27	0.0106	1	0.0393	62.00	1	0.72	1.60
	0.25	0.0098	1.020	0.0401	64.50	1.0404	0.62	1.36
	0.23	0.0090	1.04	0.0409	67.05	1.0816	0.52	1.16
	0.21	0.0082	1.06	0.0417	69.66	1.1236	0.44	0.97
	0.19	0.0074	1.080	0.0425	72.31	1.1664	0.36	0.79
	0.17	0.0066	1.1	0.0433	75.02	1.21	0.28	0.63
	0.15	0.0059	1.12	0.0440	77.77	1.2544	0.22	0.49
	22	0.4	0.0157	0.7545	0.0297	42.71	0.5693	1.76
0.35		0.0137	0.8045	0.0316	48.56	0.6472	1.34	2.96
0.30		0.0118	0.8545	0.0336	54.78	0.7302	0.99	2.17

钢网

平纹编织

目数	丝径		孔径		开孔率	开孔面积	重量	
	mm	inch	mm	inch			%	mm ²
22	0.27	0.0106	0.8845	0.0348	58.69	0.7824	0.80	1.76
	0.25	0.0098	0.904	0.0356	61.38	0.8182	0.68	1.49
	0.23	0.0090	0.924	0.0363	64.12	0.8547	0.58	1.27
	0.21	0.0082	0.944	0.0371	66.93	0.8921	0.48	1.05
	0.19	0.0074	0.9645	0.0379	69.79	0.9303	0.39	0.87
	0.17	0.0066	0.9845	0.0387	72.71	0.9693	0.31	0.69
	0.15	0.0059	1.0045	0.0395	75.70	1.0091	0.24	0.54
24	0.35	0.0137	0.708	0.0278	44.79	0.5017	1.47	3.23
	0.30	0.0118	0.758	0.0298	51.34	0.5750	1.08	2.37
	0.27	0.0106	0.788	0.0310	55.48	0.6214	0.87	1.92
	0.25	0.0098	0.808	0.0318	58.33	0.6534	0.75	1.65
	0.23	0.0090	0.828	0.0326	61.25	0.6861	0.63	1.38
	0.21	0.0082	0.848	0.0333	64.25	0.7196	0.52	1.14
	0.19	0.0074	0.868	0.0341	67.31	0.7540	0.43	0.95
	0.17	0.0066	0.888	0.0349	70.45	0.7891	0.34	0.76
	0.15	0.0059	0.908	0.0357	73.66	0.8250	0.27	0.59
	0.13	0.0051	0.928	0.0365	76.94	0.8618	0.20	0.44
0.12	0.0047	0.938	0.0369	78.60	0.8804	0.17	0.38	

钢网 平纹编织

目数	丝径		孔径		开孔率	开孔面积	重量	
	mm	inch	mm	inch	%	mm ²	kgs/m ²	lbs/m ²
30	0.35	0.0137	0.496	0.0195	34.41	0.2466	1.83	4.04
	0.30	0.0118	0.546	0.0215	41.68	0.2988	1.35	2.97
	0.27	0.0106	0.576	0.0227	46.39	0.3325	1.09	2.40
	0.25	0.0098	0.596	0.0234	49.66	0.3560	0.93	2.04
	0.23	0.0090	0.616	0.0242	53.04	0.3802	0.79	1.73
	0.21	0.0082	0.636	0.0250	56.54	0.4053	0.66	1.45
	0.19	0.0074	0.656	0.0258	60.15	0.4312	0.54	1.18
	0.17	0.0066	0.676	0.0266	63.87	0.4578	0.43	0.95
	0.15	0.0059	0.696	0.0274	67.70	0.4853	0.33	0.74
	0.13	0.0051	0.716	0.0282	71.64	0.5136	0.25	0.55
32	0.28	0.0110	0.513	0.0202	41.89	0.2639	1.25	2.75
	0.25	0.0098	0.543	0.0214	46.92	0.2956	1	2.2
	0.23	0.0090	0.563	0.0221	50.44	0.3178	0.84	1.86
	0.21	0.0082	0.583	0.0229	54.08	0.3407	0.70	1.55
	0.19	0.0074	0.603	0.0237	57.85	0.3645	0.57	1.27
	0.17	0.0066	0.623	0.0245	61.75	0.3890	0.46	1.01
35	0.3	0.0118	0.425	0.0167	34.41	0.1812	1.57	3.46
	0.28	0.0110	0.445	0.0175	37.72	0.1986	1.37	3.01

钢网

平纹编织

目数	丝径		孔径		开孔率 %	开孔面积 mm ²	重量	
	mm	inch	mm	inch			kgs/m ²	lbs/m ²
35	0.25	0.0098	0.475	0.0187	42.96	0.2263	1.09	2.40
	0.23	0.0091	0.496	0.0195	46.66	0.2457	0.93	2.04
	0.21	0.0082	0.515	0.0203	50.49	0.2659	0.77	1.69
	0.19	0.0074	0.535	0.0210	54.49	0.2869	0.63	1.38
	0.17	0.0066	0.555	0.0218	58.63	0.3088	0.50	1.11
40	0.27	0.0106	0.365	0.0143	33.03	0.1332	1.45	3.20
	0.25	0.0098	0.385	0.0151	36.75	0.1482	1.25	2.75
	0.23	0.0090	0.405	0.0159	40.67	0.1640	1.05	2.31
	0.21	0.0082	0.425	0.0167	44.79	0.1806	0.88	1.94
	0.19	0.0074	0.445	0.0175	49.11	0.1980	0.72	1.58
50	0.19	0.0074	0.318	0.0125	39.18	0.1011	0.90	1.98
	0.17	0.0066	0.338	0.0133	44.26	0.1142	0.72	1.58
	0.15	0.0059	0.358	0.0140	49.66	0.1281	0.56	1.23
60	0.17	0.0066	0.253	0.0099	35.81	0.0641	0.86	1.90
	0.15	0.0059	0.273	0.0107	41.68	0.0747	0.67	1.47
80	0.13	0.0051	0.187	0.0073	34.87	0.0351	0.67	1.48
	0.14	0.0055	0.177	0.0070	31.25	0.0315	0.78	1.72
100	0.13	0.0051	0.124	0.0049	23.83	0.0154	0.85	1.86

钢网
平纹编织



安平工厂图

总公司

万博丝网有限公司

河北省安平县丝网工业园东区纬二路 12 号

电话：0318-7568801

传真：0318-7568802

网址：www.webmeshgroup.com

分公司

万博丝网有限公司---石家庄分公司

河北省石家庄市新华区橙悦城

电话：0311-89255081

传真：0311-89255081

网址：www.webmeshgroup.com